

Condensation Control Blanket

with ECOSE® Technology

Submittal Date _____



DESCRIPTION

Knauf Insulation Condensation Control Blanket with ECOSE Technology is a resilient, flexible unfaced blanket insulation made from inorganic fibers bonded with ECOSE Technology. The blanket is suitable for application of facings for use as condensation and noise control insulation in metal buildings used for agricultural and storage applications.

ECOSE® TECHNOLOGY

ECOSE Technology is a revolutionary binder chemistry that enhances the sustainability of our products. The “binder” is the bond that holds our glass mineral wool product together and gives the product its shape and brown color. ECOSE Technology is a plant-based, sustainable chemistry that replaces the phenol/formaldehyde (PF) binder traditionally used in glass mineral wool products. Products using ECOSE Technology are formaldehyde-free and have reduced global warming potential when compared to our products of the past.

APPLICATION

When Knauf Insulation Condensation Control Blanket with ECOSE Technology is faced with a suitable vapor retarder, it can be installed in exterior wall and roof surfaces of pre-engineered metal buildings typically used for agricultural and storage applications.

PRODUCT FEATURES

Energy Conservation

- Excellent thermal properties and reduces the building’s operating costs for heating and air conditioning

Durability

- Will not rot, mold or deteriorate and will not provide sustenance for vermin, rodents or insects

SUSTAINABILITY

Knauf Insulation’s products used for thermal insulating purposes recover the energy that it took to make them in just hours or days, depending on the application. Once installed, the product continues to save energy and reduce carbon generation as long as it is in place.

Glass mineral wool insulation with ECOSE Technology contains three key ingredients:

- Recycled glass content, verified every 6 months by UL Environment
- Sand, one of the world’s most abundant resources
- Our green chemistry initiative ECOSE Technology, which is validated to be formaldehyde-free

INDOOR AIR QUALITY

- UL Environment
 - GREENGUARD certified
 - GREENGUARD Gold certified
 - Validated to be formaldehyde free

SPECIFICATION COMPLIANCE

- ASTM C553; Type I, II (Max. operating temp. 350° F)

CERTIFICATIONS

- UL Environment
 - GREENGUARD
 - GREENGUARD Gold
 - Formaldehyde Free
- EUCB

GLASS MINERAL WOOL AND MOLD

Glass mineral wool insulation will not sustain mold growth. However, mold can grow on almost any material when it becomes wet and contaminated. Carefully inspect any insulation that has been exposed to water. If it shows any sign of mold it must be discarded. If the material is wet but shows no evidence of mold, it should be dried rapidly and thoroughly. If it shows signs of facing degradation from wetting, it should be replaced.

NOTES

The chemical and physical properties of Knauf Insulation Condensation Control Blanket represent typical average values determined in accordance with accepted test methods. The data is subject to normal manufacturing variations. The data is supplied as a technical service and is subject to change without notice. References to numerical flame spread ratings are not intended to reflect hazards presented by these or any other materials under actual fire conditions.

Check with your Knauf Insulation Territory Manager to ensure information is current.



Technical Data		
Property (Unit)	Test	Performance
Corrosiveness	ASTM C665	Does not accelerate corrosion of steel
Corrosion	ASTM C1617	Pass
Combustibility	ASTM E136	Non-combustible (Blanket only)
Odor Emission	ASTM C1304	Pass
Maximum Service Temperature	ASTM C411	350 °F (177 °C)
Mold Growth	ASTM C1338	Pass
Water Vapor Sorption (by weight)	ASTM C1104	5% or less
Surface Burning Characteristics (flame spread/smoke developed)	ASMT E84, NFPA 255, and UL 723	25/50

Forms Available				
Density	Thickness	Width	Length	K-Value
0.75 PCF (12 kg/m³)	2" (51 mm)	36" (914 mm)–72" (1824 mm)	100' (30.5 m)	0.29
	2.25" (57.2 mm)	36" (914 mm)–96" (2438 mm)		
	2.5" (63.5 mm)		95' (29.0 m)	

Please contact your Territory Manager for availability.

This product is covered by one or more U.S. and/or other patents. See patent www.knaufinsulation.us/patents.

